

Technical Data Sheet

AQUAMAESTRO PRIMER

furniture and parquet primer



Description

AQUAMAESTRO PRIMER is water based acrylic colourless one-component base-coating for protection and decoration of parquet.

Typical use

It is used to protect and decorate parquet flooring, keeping its colour brighter and preventing the appearance of dark stains.

Product range

AQUAMAESTRO PRIMER

Gloss

glossy

Density

1.02 kg/l (EN ISO 2811-1)

Thinning

The coating should not be diluted!

Non-volatile-matter content

by weight: 34 % (EN ISO 3251)

Volatile organic compounds content

VOC: A(i), 140 g/l; max. 120 g/l (EN ISO 11890-1)

Compatibility

Previous coats: -

Subsequent coats: *Aquamaestro 2C PU parquet lacquer / Aquamaestro 1C PU parquet lacquer / Aquafloor lacquer for parquet and furniture*

Surface preparation

For optimal protection of wooden surfaces, proper preparation of the substrate is recommended. Surface (parquet) should be dry, cleaned from grease, impurities and sanded (finish sandpaper No.150). Clean the grinding dust with a vacuum cleaner.

AQUAMAESTRO PRIMER

furniture and parquet primer

Safety measures

Read the Safety Data Sheet before use. Keep out of reach of children. Prevent leakage and spillage into watercourses and drainage systems. Wear appropriate protective equipment when using.

Material preparation

Stir well before use!

Application

The primer can be Applied with a roller for water-based lacquers or a brush to a dry, cleaned surface free of grease and dirt, and sanded (finally with 150-grit sandpaper). After sanding, thoroughly remove all dust. Aquamaestro primer dries in 3–4 hours, after which the parquet is sanded with 220–320 grit sandpaper and the next coat of chosen lacquer can then be applied. After use thoroughly wash tools with water.

The container with any remaining lacquer after partial use must be sealed immediately.

For any additional information please contact a Chromos-Svjetlost technical advisor.

Working conditions

air temperature: $10\text{ °C} > T < 25\text{ °C}$

relative humidity: $< 75\%$

substrate temperature: $10\text{ °C} > T < 25\text{ °C}$

Spreading rate

10 m²/l for 1 layer

Drying time

surface temperature [°C]	touch dry [min]	for sanding [h]	through dry [h]	overcoating interval [h]
20	30	3 – 4	3 – 4	3 – 4

Shelf life

2 years from production date in unopened package

Transport and storage

Store in a dry and well-ventilated place out of direct sunlight at a temperature between +5 °C and 25 °C. Protect from freezing during winter.

Product and packaging disposal

Empty the packaging completely. Dispose of in accordance with valid regulations to an authorized waste collector.

AQUAMAESTRO PRIMER

furniture and parquet primer

Quality control


Product quality characteristics are determined by internal production specifications, as well as European and Croatian standards. The product is under constant supervision of factory quality control and a corresponding certificate can be issued upon request.

Disclaimers

Before using the product, please check its quality. In case of any major deviations from the declared properties of the product, stop the use and contact the manufacturer; otherwise any subsequent complaints will not be accepted.

Technical data are the result of our technical and experimental knowledge, and are provided with the intention of achieving optimal results in working with Chromos-Svjetlost products. The data does not contain a legal or secondary obligation of the manufacturer nor does it release the user from the obligation to check the suitability of the product for particular purpose. Due to the use of natural raw materials in our products, minor deviations from certain values are possible for individual deliveries. Contact our Technical service before use on substrates not listed in the accompanying documentation. The manufacturer reserves the right to make any subsequent changes to the Technical Data Sheet. Only the latest edition is valid. Updated Technical Data Sheets can be found on the website www.chromos-svjetlost.hr or can be requested from the manufacturer via the contact e-mail address below. Contact our Technical service for more detailed information. Read the safety labels on the product packaging before use. Safety Data Sheet is available on request via e-mail: msds@chromos-svjetlost.hr.

O 8.3/2//1 | 20.04.2026.



Quality and Environmental management systems certified in accordance with TÜV Nord;
Certificate No: 44 100 134668 / 44 104 134668